

Nickel Alloy Wire

Alloy: WWG-30
Class: ERNiCrMo-11

Conforms to Certification: AWS A5.14
ASME SFA A5.14

Alloy: ERNiCrMo-11 (Alloy G-30)
Weld Process: GMAW, GTAW Welding Processes

AWS Chemical Composition Requirements

C = 0.03 max	Cu = 1.0 – 2.4
Mn = 1.5 max	Ni = Remainder
Fe = 13.0 – 17.0	Co = 5.0 max
P = 0.04 max	Cr = 28.0 – 31.5
S = 0.02 max	Mo = 4.0 – 6.0
Si = 0.80 max	Nb+Ta = 0.30 – 1.50
Other = 0.50 max	W = 1.5 – 4.0

Deposited All Weld Metal Properties % (AW)

Tensile Strength	89,000psi
Elongation	28%

Deposited Chemical Composition % (Typical)

C = 0.02	Co = 3.50	Ni = Balance
Mn = 0.90	Cu = 1.75	Cr = 29.5
Fe = 15.5	W = 2.10	Mo = 5.0

Deposited Charpy-V-Notch Impact Properties %

Not applicable

Application

ERNiCrMo-11 is used for welding nickel-chromium-molybdenum base materials to themselves, steel and other nickel base alloys.

Recommended Welding Parameters for TIG and MIG Welding of Nickel Alloys

<u>Process</u>	<u>Diameter of Wire</u>	<u>Voltage (V)</u>	<u>Amperage (A)</u>	<u>Gas</u>
Tig	.035 inches x 36	12 -15	60 -90	100% Argon
	.045 inches x 36	13 -16	80 - 110	100% Argon
	1/16 inches x 36	14 - 18	90 - 130	100% Argon
	3/32 inches x 36	15 – 20	120 -175	100% Argon
	1/8 inches x 36	15 – 20	150 - 220	100% Argon
MIG	.035 inches	26 – 29	150 – 190	75% Argon + 25% Helium
	.045 inches	28 – 32	180 – 220	75% Argon + 25% Helium
	1/16 inches	29 – 33	200 - 250	75% Argon + 25% Helium

Note: Other shielding Gases may be used for Mig and Tig welding. Shielding gases are chosen taking Quality, cost, and Operability into consideration.

