

FLUX CORED STAINLESS STEEL ELECTRODE DM317L

Classification: ER317L AWS A5.9 / ASME SFA 5.9

Description, Characteristics & Applications:

ER317L is used for welding stainless steels with similar composition. Due to its higher molybdenum content, this alloy offers high resistance to pitting and crevice corrosion. Lower carbon makes the weld metal less susceptible to inter-granular corrosion.

Typical Chemical Composition (%)

C	Cr	Ni	Mo	Mn	Si	P	S	Cu
0.03 max	18.5 - 20.5	13.0 - 15.0	3.0 - 4.0	1.0 - 2.5	0.30 - 0.65	0.03 max	0.03 max	0.75 max

Deposited Chemical Composition (%)

C	Cr	Ni	Mo	Mn	Si	P	S	Cu
0.02	18.50	13.20	3.40	1.70	0.40	0.010	0.012	---

Typical Mechanical Properties as Welded

Tensile Strength	Yield Strength	Elongation (%)	Hardness	Ferrite WRC (FN)	CVN Impacts (J) @ °C
87,000psi	55,000psi	47%	-----	-----	-----

Notes The following welding data are typical for MIG welding with Argon + 2% oxygen and TIG welding with Argon as shielding gas. Submerged arc results depend on the type of flux used.

Short Arc Welding / Spray Arc Welding

Process	Diameter	Wire Feed	Amps	Volts	Shielding Gas	CFH
SHORT ARC	.030	13-26	40-120	16-20	Argon + 2% O ²	25
	.035	13-26	60-140	16-22	Argon + 2% O ²	25
SPRAY ARC	.035	20-39	140-220	24-29	Argon + 2% O ²	38
	.045	16-30	160-260	25-30	Argon + 2% O ²	38
	1/16	10-16	230-350	27-31	Argon + 2% O ²	38

TIG Welding Parameters

Diameter	Amps DCEN	Voltage	Gases
.035	60-90	12-15	Argon 100%
.045	80-110	13-16	Argon 100%
1/16	90-130	14-16	Argon 100%
3/32	120-175	15-20	Argon 100%

Note: Parameters for TIG welding are dependent upon plate thickness and welding position. Other shielding gases may be used for MIG and TIG welding; gases are selected by considering quality, cost, and operability.

Submerged Arc Welding Parameters

Wire Diameter	Amps	Voltage
3/32	250-450	28-32
1/8	300-500	29-34
5/32	400-600	30-35
3/16	500-700	30-35

Both agglomerated and fused fluxes can be used for submerged arc welding. The chemical composition of the flux affects the chemistry of the weld metal and, consequently, its corrosion resistance and mechanical properties.

The above information is to be used as a guideline and is based on the source Product Data Sheet. If additional information is needed please contact (800) 692-5930.