

## STAINLESS STEEL BARE WIRE DM308

**Classification:** ER308 AWS A5.9 / ASME SFA 5.9

### Description, Characteristics & Applications:

ER308 filler metal is used for TIG, MIG, and submerged arc welding of unstabilized stainless steels such as Types 301, 302, 304, 305, and 308. This filler metal is among the most popular stainless steel grades and is used for general-purpose applications where corrosion conditions are moderate.

### Typical Chemical Composition (%)

C	Cr	Ni	Mo	Mn	Si	P	S	Cu	N
0.08 max	19.5 - 22.0	9.0 - 11.0	0.75 max	1.0 - 2.5	0.30 - 0.65	0.03 max	0.03 max	0.75 max	---

### Deposited Chemical Composition (%)

C	Cr	Ni	Mo	Mn	Si	P	S	Cu	N
0.04	20.0	9.5	---	1.8	0.30	0.009	0.009	---	0.05

### Deposited All Weld Metal Properties % (AW)

Tensile Strength	Yield Strength	Elongation $\bar{A}$ (%)	Hardness	Ferrite WRC (FN)	Area of Reduction	CVN Impacts (J)
						@ °C
90,000psi	48,000psi	40%	-----	-----	60%	-----

**Notes**

Data are typical for ER308 weld metal deposited by MIG using Argon + 2% oxygen and TIG using 100% Argon as shielding gas. Submerged arc results depend on the type of flux used.

### Short Arc Welding / Spray Arc Welding

Process	Diameter	Wire Feed	Amps	Volts	Shielding Gas	CFH
SHORT ARC	.030	13-26	40-120	16-20	Argon + 2% O <sub>2</sub>	25
	.035	13-26	60-140	16-22	Argon + 2% O <sub>2</sub>	25
SPRAY ARC	.035	20-39	140-220	24-29	Argon + 2% O <sub>2</sub>	38
	.045	16-30	160-260	25-30	Argon + 2% O <sub>2</sub>	38
	1/16	10-16	230-350	27-31	Argon + 2% O <sub>2</sub>	38

### TIG Welding Parameters

Diameter	Amps DCEN	Voltage	Gases
.035	60-90	12-15	Argon 100%
.045	80-110	13-16	Argon 100%
1/16	90-130	14-16	Argon 100%
3/32	120-175	15-20	Argon 100%

Note: Parameters for TIG welding are dependent upon plate thickness and welding position. Other shielding gases may be used for MIG and TIG welding; gases are selected by considering quality, cost, and operability.

### Submerged Arc Welding Parameters

Wire Diameter	Amps	Voltage
3/32	250-450	28-32
1/8	300-500	29-34
5/32	400-600	30-35
3/16	500-700	30-35

For additional information please visit our website at [Duramax-weld.com](http://Duramax-weld.com) or email [info@duramax-weld.com](mailto:info@duramax-weld.com)